

Diameter: .052

AWS D1.8 Seismic Certificate of Conformance

This is to certify that the product stated below is of the same classification, manufacturing process, and material requirements as the electrode used for the testing on the date stated. All tests required by the specifications for classification were performed and the material met all requirements. It was manufactured and supplied according to the quality management system of Select-Arc, Inc., which meets the requirements of ISO 9001 and other applicable specifications. This certificate complies with the requirements of EN 10204, Type 2.2.

Product: Select 70C-6LS

Test Completion Date: 5/18/2020

Diameter(s): .052

Lot Numbers: (.052) 5485

Lot Class: 'T4' per AWS A5.01

Certificate Expiration Date: 5/18/2023

Specifications: AWS D1.8: 2016

Classification: E70C-6M

Weld Parameters - High Heat Input

Lot Number:	5485
Electrode Diameter:	.052
Shielding Gas	90%Ar / 10%CO2
Amperage:	359.0
Arc Voltage:	28.0
Current Polarity:	DCEP
CTWD (in):	3/4
No. of Passes/Layers:	7/4
Interpass Temperature(°F):	450
Heat Input Avg.(kJ/in.):	71.1

Mechanical Properties - High Heat Input

Lot Number:		5485
Shielding Gas		90%Ar / 10%CO2
Requirements		Results
Test Condition:	As-Welded	As-Welded
PWHT Temperature:	-	-
Tensile Strength (psi):	70000 min	79000
Yield Strength (psi):	58000 min	62000
Elongation (%):	22 min	31
Charpy V-Notch Impacts:		98, 96, 88
ft-lb f @ 70°F	40 avg.	94 avg
Charpy V-Notch Impacts:		55, 58, 57
ft-lb f @ 32°F	40 avg.	56 avg

Weld Parameters - Low Heat Input

Lot Number:	5485
Electrode Diameter:	.052
Shielding Gas	90%Ar / 10%CO2
Amperage:	275.0
Arc Voltage:	27.0
Current Polarity:	DCEP
CTWD (in):	3/4
No. of Passes/Layers:	16/8
Interpass Temperature(°F):	250
Heat Input Avg.(kJ/in.):	29.7


Mechanical Properties - Low Heat Input

Lot Number:		5485
Shielding Gas		90%Ar / 10%CO2
Requirements		Results
Test Condition:	As-Welded	As-Welded
PWHT Temperature:	-	-
Tensile Strength (psi):	70000 min	87000
Yield Strength (psi):	58000 min	75000
Elongation (%):	22 min	27
Charpy V-Notch Impacts:		82, 77, 82
ft-lb f @ 70°F	40 avg.	80 avg
Charpy V-Notch Impacts:		63, 71, 71
ft-lb f @ 32°F	40 avg.	68 avg

This product meets the requirements for a 2 week exposure at 80°F, 80% humidity (per Annex E of AWS D1.8:2016)

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification.

Signed By: _____



Joshua S Westerheide, Quality Manager