

AWS D1.8 Seismic Certificate of Conformance

This is to certify that the product stated below is of the same classification, manufacturing process, and material requirements as the electrode used for the testing on the date stated. All tests required by the specifications for classification were performed and the material met all requirements. It was manufactured and supplied according to the quality management system of Select-Arc, Inc., which meets the requirements of ISO 9001 and other applicable specifications. This certificate complies with the requirements of EN 10204, Type 2.2.

Product: Select 70C-6LS
Diameter(s): 1/16
Lot Class: ' T4 ' per AWS A5.01
Specifications: AWS D1.8:2021

Test Completion Date: 8/29/2022
Lot Numbers: (1/16) 1615
Certificate Expiration Date: 8/29/2025

Weld Parameters - High Heat Input

Lot Number:	1615
Electrode Diameter:	1/16
Shielding Gas	75%Ar / 25%CO2
Amperage:	322.0
Arc Voltage:	29.5
Current Polarity:	DCEP
CTWD (in):	3/4
No. of Passes/Layers:	8/5
Interpass Temperature(°F):	450
Heat Input Avg.(kJ/in.):	70.7

Mechanical Properties - High Heat Input

Lot Number:		1615
Shielding Gas		75%Ar / 25%CO2
Requirements		Results
Test Condition:	As-Welded	As-Welded
PWHT Temperature:	-	-
Tensile Strength (psi):	70000 min	84000
Yield Strength (psi):	58000 min	66000
Elongation (%):	22 min	29
Charpy V-Notch Impacts:		42, 38, 43
ft-lb f @ 32°F	40 avg. min	41 avg
Charpy V-Notch Impacts:		55, 73, 64
ft-lb f @ 70°F	40 avg. min	64 avg

Weld Parameters - Low Heat Input

Lot Number:	1615
Electrode Diameter:	1/16
Shielding Gas	75%Ar / 25%CO2
Amperage:	310.0
Arc Voltage:	27.0
Current Polarity:	DCEP
CTWD (in):	3/4
No. of Passes/Layers:	15/7
Interpass Temperature(°F):	250
Heat Input Avg.(kJ/in.):	31.2


Mechanical Properties - Low Heat Input

Lot Number:		1615
Shielding Gas		75%Ar / 25%CO2
Requirements		Results
Test Condition:	As-Welded	As-Welded
PWHT Temperature:	-	-
Tensile Strength (psi):	70000 min	91000
Yield Strength (psi):	58000 min	79000
Elongation (%):	22 min	26
Charpy V-Notch Impacts:		47, 53, 50
ft-lb f @ 32°F	40 avg. min	50 avg
Charpy V-Notch Impacts:		79, 71, 74
ft-lb f @ 70°F	40 avg. min	74 avg

This product meets the requirements for a 2 week exposure at 80°F, 80% humidity (per Annex E of AWS D1.8)

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification.

Signed By: _____



Joshua S Westerheide, Quality Manager