

Diameter: 3/32

## AWS D1.8 Seismic Certificate of Conformance

This is to certify that the product stated below is of the same classification, manufacturing process, and material requirements as the electrode used for the testing on the date stated. All tests required by the specifications for classification were performed and the material met all requirements. It was manufactured and supplied according to the quality management system of Select-Arc, Inc., which meets the requirements of ISO 9001 and other applicable specifications. This certificate complies with the requirements of EN 10204, Type 2.2.

Product: Select 70TR

Test Completion Date: 11/29/2019

Diameter(s): 3/32

Lot Numbers: (3/32) 0670 1732 1785

Specifications: AWS D1.8:2016

Certificate Expiration Date: 11/29/2022

Classification: E70T-1C, E70T-9C

### Weld Parameters - High Heat Input

Lot Number:	0670	1732	1785
Electrode Diameter:	3/32	3/32	3/32
Shielding Gas	CO2	CO2	CO2
Amperage:	428.0	419.0	458.0
Arc Voltage:	32.0	32.0	33.0
Current Polarity:	DCEP	DCEP	DCEP
CTWD (in):	1	1	1
No. of Passes/Layers:	9/5	9/5	8/4
Interpass Temperature(°F):	450	450	450
Heat Input Avg.(kJ/in.):	70	72	74.8

### Mechanical Properties - High Heat Input

Lot Number:		0670	1732	1785
Shielding Gas		CO2	CO2	CO2
<b>Requirements</b>		<b>Results</b>	<b>Results</b>	<b>Results</b>
Test Condition:	As-Welded	As-Welded	As-Welded	As-Welded
PWHT Temperature:	-	-	-	-
Tensile Strength (psi):	70000 min	76000	81000	86000
Yield Strength (psi):	58000 min	62000	67000	68000
Elongation (%):	22 min	31	28	26
Charpy V-Notch Impacts:		125, 121, 117	105, 103, 98	63, 75, 72
ft-lb f @ 70°F	40 avg.	121 avg	102 avg	70 avg
Charpy V-Notch Impacts:		71, 72, 78	56, 56, 62	50, 51, 52
ft-lb f @ 32°F	40 avg.	74 avg	58 avg	51 avg

### Weld Parameters - Low Heat Input

Lot Number:	0670	1732	1785
Electrode Diameter:	3/32	3/32	3/32
Shielding Gas	CO2	CO2	CO2
Amperage:	307.0	335.0	319.0
Arc Voltage:	28.0	28.0	28.0
Current Polarity:	DCEP	DCEP	DCEP
CTWD (in):	1	1	1
No. of Passes/Layers:	18/9	18/9	16/8
Interpass Temperature(°F):	250	250	250
Heat Input Avg.(kJ/in.):	32.2	33.1	34


### Mechanical Properties - Low Heat Input

Lot Number:		0670	1732	1785
Shielding Gas		CO2	CO2	CO2
<b>Requirements</b>		<b>Results</b>	<b>Results</b>	<b>Results</b>
Test Condition:	As-Welded	As-Welded	As-Welded	As-Welded
PWHT Temperature:	-	-	-	-
Tensile Strength (psi):	70000 min	87000	88000	85000
Yield Strength (psi):	58000 min	75000	77000	73000
Elongation (%):	22 min	27	26	27
Charpy V-Notch Impacts:		103, 106, 100	69, 68, 60	104, 104, 110
ft-lb f @ 70°F	40 avg.	103 avg	66 avg	106 avg
Charpy V-Notch Impacts:		70, 62, 74	45, 49, 49	81, 84, 89
ft-lb f @ 32°F	40 avg.	69 avg	48 avg	85 avg

This product meets the requirements for a 2 week exposure at 80°F, 80% humidity (per Annex E of AWS D1.8:2016)

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification.

Signed By: \_\_\_\_\_



Joshua S Westerheide, Quality Manager